

## 28650

### 5 mil Instant Dry Solvent White Film - Gloss

#### PRODUCT DESCRIPTION

28650 - Is a polyester film with a high gloss finished that will yield instant dry images when printed with eco solvent and latex inkjet inks.

FEATURE	ADVANTAGE	BENEFIT
5 mil Polyester No-Tear Base	Very Durable	Long Lasting Graphics
Bright White Base	High Opacity - without greyback	Economical Choice
Instant Dry	No print damage from handling	Faster Production
High Gloss Photo Finish	Outstanding Print Quality	Satisfied Customers
Lay Flat	Reduce curl and cupping	Use not laminated
Solvent/Latex Inkjet Compatible	Reduce SKUS	Save Money
Durable top layer	Eliminate Scratching	Long Lasting

#### SPECIFICATIONS

Caliper	5 mil
Construction	White Polyester Film
Whiteness	100 (We)
Gloss (60°)	45
Opacity	95%

\*All values listed are target values

#### PRINTERS

EPSON® GS6000  
 Hewlett-Packard® DJ 8000s, 9000s, 10000s  
 Hewlett-Packard® L25500, L65500  
 Mimaki® JV3, JV33, JV 5  
 Mutoh® ValueJet  
 Roland® AJ  
 Roland® VP, SP, XC, XJ, SJ

#### Ink

Eco-Solvent Inks  
 Low-Solvent  
 Latex Inks  
 ES, SS2, SS2-1, HS  
 Eco-Solvent Inks  
 Eco-Xtreme  
 ECO-SOL MAX

Most: Latex, Eco, Mild/Mid, True Solvent Inkjet Printers

#### FINISHING RECOMENDATIONS

Use low melt or pressure sensitive laminates to extend the life of the print and increase its durability.  
 Allow 24 hours for ink to cure before finishing graphic.

#### STORAGE CONDITIONS

Temperature 59°-86°F (15°-30°C).  
 Re-pack opened rolls when not in use.  
 One year shelf life at conditions noted above.  
 Allow material to stabilize to room conditions for 24 hours before use.